

Technical Data Sheet




211
ANTI-SKID
GREY ADHESIVE

211 ANTI-SKID GREY ADHESIVE



**ADVANCED
POLYMER
ENRICHED**



JKTylo 211 Anti-Skid Grey Adhesive is an advanced polymer enriched cement based tile adhesive, suitable for application of ceramic tiles and natural stones for interior floors, interior walls upto 3 meters and vitrified tiles for interior floor applications. It is also suitable for tile on tile application. This product is recommended for various concrete and cement-based substrates.

Area of Application

This product is a polymer modified, thin set adhesive designed for fixing ceramic tiles, semi - vitreous tiles and natural stones of regular size in dry application on interior floor and interior walls upto 3 meters. Also suitable for vitrified tiles on floors and tile on tile application. It is suitable for various cement and concrete based substrates. It can be used upto 12mm bed thickness.

Substrates

- Cement Screed
- Cement Plaster
- Concrete masonry
- Cement mortar beds
- Brick masonry
- Cement terrazzo
- Existing ceramic tiles*
- Existing natural stones*

* Surface should be cleaned and roughened before application of tiles or stones.

Key Benefits and Features

- Interior application, polymer based
- Better workability and durability
- Superior adhesion
- High strength
- No water curing required
- Quick application
- Convenient to use
- Single component, just add water

- Standard open time
- Complies with EN/ISO C1T classification
- As per IS 15477:2019 - Type 1T standard
- Fortify with latex compound for external applications**
- No VOC - for healthy living

** Consult with JKTylo technical team for external applications.

Typical Properties

Color	Grey
Powder Density	1.34 - 1.52 Kg/Litre
Open Time	15 ± 5 Minutes
Adjustment Time	15 ± 5 Minutes
Pot Life	90 - 120 Minutes


Water-Powder Ratio	23% - 25%
Foot Traffic/ Ready To Use	24 Hours

Note : Result depends on weather and site conditions

Application Method

1. Surface Preparation

- Surfaces temperature should be cool before application, ideally below 35 degrees.
- Surface should be structurally sound and free from dirt, oil, grease, loose peeling paint, concrete sealer or curing compound.
- All slabs must be plumb and true with in: Walls – 3mm in 2.5m, and Floors – 1.5mm in 1.0m
- Rough or uneven concrete surfaces should be made smooth with Screed/Plaster material. Use a wood float for better finish.
- Dry, dusty concrete slabs or masonry should be dampened and excess water should be swept off.



Installation may be made on a damp surface.

- New concrete slabs shall be damp cured and should be 28 days old before application.

2. Mixing and Blending

- Take 4.5 to 5.0 Litres of potable water into a clean container.
- Gradually mix 20 Kg JKTylo with slow speed mixer to get a uniform lump-free paste in workable consistency.
- Allow paste to settle for 5-10 minutes. Adjust consistency, if necessary.
- Mixed paste should be used within 90-120 minutes.



Contd..

Application Method

3. Fixing Application

- Apply adhesive uniformly on a substrate to a desired thickness with flat side of notch trowel. Comb with a notch trowel using notched side.
- Use proper size of notched trowel to ensure full bedding of the tile.
- Spread as much adhesive paste as it can be tiled within 10 minutes.
- Press the tile against the applied tile adhesive and fix it by using rubber mallet. Imbed tile and adjust level.
- Ensure that back of the tile is fully covered with the tile adhesive.
- Ensure adequate gap between tiles/stones to




accommodate thermal expansion and contraction.

- As required one can use spacer to provide grout joints between tiles/stones. Remove the spacers when the adhesive is firmly set.
- If the Tile adhesive is dried and skinned, then adhesive should be removed and replaced with a fresh adhesive.

4. Grouting

- Grouting should be carried out after 24 hours from the time of tile installation.
- Grout with JKTylo Cementitious Grout.
- For stain resistance, use JKTylo Epoxy Grout.



Technical Information

Test specification requirement as per IS 15477:2019

S.No.	Test Property	Test Method	Specification	Typical Value
1	Tensile Adhesion (N/mm²)			
	(a) Dry Condition - 28 days	IS 15477:2019 Annex A (Clause 5.1)	Min. 0.5 N/mm ²	0.6 - 0.8 N/mm ²
	(b) Wet Condition - 21 days	IS 15477:2019 Annex A (Clause 5.1)	NA	NA
2	Shear Adhesion (N/mm²)			
	(a) Dry Condition - 28 Days	IS 15477:2019 Annex B (Clause 5.2)	Min. 1.0 N/mm ²	1.2 - 1.5 N/mm ²
	(b) Heat Ageing Conditions - 28 Days	IS 15477:2019 Annex B (Clause 5.2)	NA	NA
	(c) Wet Condition - 28 Days	IS 15477:2019 Annex B (Clause 5.2)	NA	NA
3	Slip (required for vertical application only)	IS 15477:2019 Annex E (Clause 5.5)	Shall not be more than 0.5 mm	0.1 - 0.3 mm
4	Deformability (required for vertical application only)			
	(a) Deformable adhesive S1	IS 15477:2019 Annex F (Clause 5.6)	≥ 2.5 mm, < 5.0 mm	NA
	(b) Highly Deformable Adhesive S2	IS 15477:2019 Annex F (Clause 5.6)	≥ 5.0 mm	NA

Technical Information

Test specification requirement as per EN 12004 & ISO 13007

S.No.	Test Property	Test Method	Specification	Typical Value
1	Open Time : Tensile Adhesion Strength (N/mm²)			
	(a) After 5 Minute	EN 1346		0.75 - 0.89 N/mm ²
	(b) After 20 Minute	EN 1346	≥ 0.5 N/mm ² After not less than 20 minute	0.5 - 0.60 N/mm ²
	(c) After 30 Minute	EN 1346	≥ 0.5 N/mm ² After not less than 30 minute	NA
2	Tensile Adhesion Strength (N/mm²)			
	(a) Dry Conditions - 28 Days	EN 1348	≥ 0.5 N/mm ²	0.6 - 0.80 N/mm ²
	(b) Water Immersion Conditions - 28 Days	EN 1348	≥ 0.5 N/mm ²	0.55 - 0.70 N/mm ²
	(c) Heat Ageing Conditions - 28 Days	EN 1348	≥ 0.5 N/mm ²	0.65 - 0.90 N/mm ²
3	Slip Resistance (for vertical application)	EN 1308	≤ 0.5mm	0.28 mm
4	Transverse Deformation			
	(a) Deformable Adhesive - S1	EN 12002	≥ 2.5 mm, < 5 mm	NA
	(b) Highly Deformable Adhesive - S2	EN 12002	≥ 5 mm	NA

Packing : 20 Kg BOPP Bags

Coverage : Approx 50-55* sq.ft. per 20 Kg bag when applied by notch trowel of size 1/4" x 1/4" (6mm x 6mm) square notched trowel at an average thickness of 3mm.

* Coverage depends upon trowel notch size, type and size of tiles and substrate evenness and smoothness

Shelf Life : 12 months from the date of manufacturing, when stored in dry area.

Note: Actual coverage and field performance will depend on installation method and site conditions.

Disclaimer :

The company provides guarantee against defective material, but the application and usage of products are made without guarantee since the application conditions are not in its control. All products are tested under the recommended conditions of temperature $27 \pm 2^{\circ}\text{C}$ and humidity $65 \pm 5\%$. Company recommends to verify the suitability of product for intended use with the latest version of data sheet. The company may modify product data sheet without any prior notice. All technical characteristics are listed for guidance only and JK Tylo technical team may be contacted for more information.



Registered Office : Kamla Tower, Kanpur - 208001

Ph. : 0512-2371478-85, Fax : 0512-2399854 E-mail : admin@jkcement.com

Corporate Office : Prism Tower, 5th Floor, Ninaniya Estate, Gwal Pahari,
Gurugram - 122102, Haryana Tel : +(91)124-6919000

Website : www.jkcement.com **Toll Free No. :** 1800 102 8868

Customer Care : customercare.white@jkcement.com

